

●定番品特性表(布帛) ● Base cloth 1. (Woven Fabric)

項目 Item		品番 Product Number	102N	102C	175N	175C	302N	673N	673C	973N
繊維素材 Material			ポリエステル平織物 Spun Polyester (plain)		ポリエステル平織物 Spun Polyester (plain)		ポリエステル ジューゼット Multi filament polyester (crepe)	アクリルタフタ Acryl filamet (plain)		難燃アクリル 平織物 Spun modacryl (plain)
密度 (本/inch) Construction (Finish)	経 Warp		68	68	68	68	108	84	84	112
	緯 Weft		60	60	60	60	84	70	70	60
番手 Yarn count	経 Warp		30	30	30	30	50 ^D (48 ^F)	75 ^D (40 ^F)	75 ^D (40 ^F)	40
	緯 Weft		30	30	30	30	50 ^D (48 ^F)	75 ^D (40 ^F)	75 ^D (40 ^F)	40
メッキ金属 Metal types			ニッケル Ni	ニッケル Ni	銅+ニッケル Cu&Ni	銅+ニッケル Cu&Ni	ニッケル Ni	銅+ニッケル Cu&Ni	銅+ニッケル Cu&Ni	銅+ニッケル Cu&Ni
メッキ率 (%) Metal add on (%)			20	20	50	50	20	30	30	30
全幅 (cm) Total width (cm)			114	114	114	114	114	114	114	114
メッキ有効幅 (cm) Available width (cm)			100	100	100	100	100	100	100	100
長さ (m) Length (m)			100	100	100	100	100	100	100	100
厚さ (mm) Fabric thickness (mm)			0.18	0.18	0.18	0.18	0.13	0.10	0.10	0.20
表面抵抗 (Ω/□) Metal surface resistance (Ω/□)			0.2~0.5	1.0以下	0.04~0.00	0.1以下	0.5以下	0.1以下	0.3以下	0.08以下
表面コーティング Coating finish			無 Non coating	有 Resin coating	無 Non coating	有 Resin coating	無 Non coating	無 Non coating	有 Resin coating	無 Non coating

※コーティングを施したものは表面抵抗の測定値が悪く表示されますが、コーティング加工前の表面抵抗値は、コーティング無しのもと同じです。

※性能等の数値は測定値であり保証値ではありません。

※ Although the measured value of the surface resistance is shown poorly for the products that have undergone coating, the surface resistance values prior to their undergoing of the coating process were the same as that of products without surface coatings.

※ The values for expressing the performance of the products are measured values, and are not guaranteed performance values.